

**CARICHI LASTRE FIBROCEMENTO RETTE / CURVE**

Interasse (m)	Luce (m)	C.uniforme di rottura (daN/mq)	C.ammissibile Coeff.Sicur.2.5
0,60	0,55	2971	1116
0,65	0,60	2325	930
0,70	0,65	1994	798
0,75	0,70	1709	684
0,80	0,75	1495	598
0,85	0,80	1308	523
0,90	0,85	1163	465
0,95	0,90	1034	414
1,00	0,95	930	372
1,05	1,00	837	335
1,10	1,05	761	304
1,15	1,10	692	277
1,20	1,15	634	254
1,25	1,20	581	232
1,30	1,25	537	215
1,35	1,30	495	198
1,40	1,35	460	184
1,45	1,40	427	171
1,50	1,45	399	160
1,55	1,50	372	149
1,60	1,55	349	140
1,65	1,60	327	131
1,70	1,65	308	123
1,75	1,70	290	116
1,80	1,75	274	110
1,95	1,80	258	103
2,00	1,85	245	98
2,05	1,90	232	93
2,10	1,95	220	88
2,15	2,00	209	84
2,20	2,05	199	80
2,25	2,10	190	76
2,30	2,15	181	72
2,35	2,20	173	69
2,40	2,25	165	66
2,45	2,30	158	63
2,50	2,35	152	61
2,55	2,40	145	58
2,60	2,45	140	56

